



THE #1 CHOICE OF
PAINTING PROFESSIONALS®

ENDURAGLOSS®

Rust-Preventative Silicone Alkyd Gloss Enamel 42-53A



DESCRIPTION: ENDURAGLOSS® is a premium exterior/interior, silicone alkyd gloss enamel designed for use on all properly prepared and primed metal. ENDURAGLOSS is recommended for surfaces exposed to severe conditions, such as seacoast areas. ENDURAGLOSS provides outstanding corrosion resistance, abrasion resistance, and overall durability when applied over a rust-inhibitive primer. Not recommended for exterior wood. **Note:** When used in areas of low light, ENDURAGLOSS is subject to yellowing in white and other light colors. Within California, available only in quarts. **FOR METAL SUBSTRATES ONLY.**

PRODUCT INFORMATION

SOLVENT TYPE: Paint thinner		RESIN TYPE: Silicone alkyd	
FINISH (ASTM D 523): Gloss: 85-90% on a 60° meter			
COLORS: Stock colors: White and Black. Other colors can be special ordered.			
TINT BASES: L Tintable White, M Medium, U Ultra Deep			
VISCOSITY@77°F/25°C (ASTM D 562): 85-90 KU			
MAXIMUM VOC CONTENT 400 g/L (as supplied)		MAXIMUM RAVOC (Reactivity-Adjusted VOC) 175 g/L	
SOLIDS BY VOLUME (ASTM D 2697) 49.2% ± 2%		SOLIDS BY WEIGHT 64.5% ± 2%	
WEIGHT PER GALLON (ASTM D 1475): 9.34 lbs.			
COMPOSITION BY WEIGHT			
Pigment-23.1%		Vehicle-76.9%	
*Prime pigments22.0		Alkyd resins40.1	
Reinforcing pigments1.1		Thinner & additives36.8	
<i>*Prime pigments include titanium dioxide (TiO₂), plus all other pigments directly adding to the hiding power of this paint.</i>			
RECOMMENDED FILM THICKNESS PER COAT			
Wet: 4.1 mils		Dry: 2.0 mils	
PRACTICAL COVERAGE PER COAT AT RECOMMENDED DRY FILM THICKNESS Approximately 325-375 sq. ft. per gallon, depending on surface conditions and application techniques.			
THINNING RECOMMENDATION: This coating is intended to be applied without thinning or diluting under normal environmental and application conditions.			
AVERAGE DRY TIME@77°F/25°C (ASTM D 1640) To touch: 3-4 hours Recoat: 24 hours Dry times and recoat times are temperature, humidity and film thickness dependent.			
APPLICATION EQUIPMENT: Brush, roller, airless spray, HVLP spray, electrostatic spray			
PACKAGING: Quart, one-gallon containers			
STORAGE: Store in a dry area. Protect from freezing. Protect from temperatures above 110°F for extended periods of time. Extreme temperatures may cause paint to become unusable. See <i>Paint Storage Best Practices</i> Technical Bulletin at dunnedwards.com for more information.			
CLEANUP: Paint thinner where allowed. Otherwise, use acetone.			
DISPOSAL: For information on local options to dispose of unwanted leftover paint, call Dunn-Edwards Customer Service at 1-888-DEPAINT or visit www.dunnedwards.com . Do not mix with other products.			
SAFETY DATA SHEET: Available at www.dunnedwards.com			

SURFACE PREPARATION: All surfaces must be cured, clean, dry, and free from dirt, dust, rust, stains, grease, oil, mildew, wax, efflorescence, bond-breakers, and other contaminants. Remove all loose, peeling, or chalky paint by sanding, scraping, or other appropriate methods. Repair all cracks, holes, and other surface imperfections with a suitable patching material. Repaired surfaces should then be sanded smooth and dusted clean. Glossy surfaces should be dulled to provide a roughened surface for good adhesion.

SPECIAL INSTRUCTIONS

- CAUTION: Scraping or sanding surfaces of older buildings (especially pre-1978) may release dust containing lead or asbestos. EXPOSURE TO LEAD OR ASBESTOS CAN BE VERY HAZARDOUS TO YOUR HEALTH. Always wear appropriate personal protective equipment during surface preparation, and finish cleanup of any residues by water-washing all surfaces. For more information, see Dunn-Edwards brochure on "Surface Preparation Safety" or call EPA's National Lead Information Hotline at 1-800-424-LEAD, or log onto www.epa.gov/lead/or/asbestos, or contact your state or local Health Department.
- This product can neither cause nor prevent or cure the growth of mold, mildew, or other forms of fungus. Excessive moisture and inadequate ventilation are the main conditions that promote their growth. Correct any such conditions before painting.
- All galvanized metal must be solvent cleaned to remove oil, grease, and other contaminants prior to etching. Surface should then be etched with a suitable etching solution.
- Do not apply when the air or surface temperature is below 50°F.
- ENDURAGLOSS is recommended for use in preventing the corrosion of metal substrates.
- In California, 42-53A is available in quarts only.

CALIFORNIA PROPOSITION 65 NOTICE:

WARNING: This product can expose you to ethylbenzene, which is known to the State of California to cause cancer. For more information go to www.P65Warnings.ca.gov.

PRIMERS

METAL

- | | |
|--------------|---------------------------------------------------------------------------------------------------------------------------------|
| Ferrous: | ULTRA-GRIP® Premium (UGPR00)-INTERIOR ONLY, BLOC-RUST® Premium (BRPR00) or ULTRASHIELD® Galvanized Metal Primer (ULGM00) |
| Non-ferrous: | ULTRASHIELD® Galvanized Metal Primer (ULGM00) or ULTRA-GRIP® Premium (UGPR00) |