



THE #1 CHOICE OF
PAINTING PROFESSIONALS®

ACRI-HUES®

Exterior Semi-Gloss Paint ACHS50



DESCRIPTION: ACRI-HUES® Semi-Gloss is a professional exterior, ultra-low VOC, acrylic semi-gloss paint. It is ideal for use on a wide range of residential and commercial projects. ACRI-HUES Semi-Gloss provides good hide, block resistance, adhesion, and dirt pick-up resistance, and can be used on properly prepared and primed masonry, stucco, wood, trim and doors, and metal. ACRI-HUES Semi-Gloss can be used on properly prepared and primed interior masonry, concrete, wood, and metal. Can be used down to surface and air temperature of 35°F.

PRODUCT INFORMATION

SOLVENT TYPE: Waterborne		RESIN TYPE: Acrylic	
FINISH (ASTM D 523): Semi-Gloss: 40–50% on a 60° meter			
COLORS: All colors can be special ordered or store mixed.			
TINT BASES: L Tintable White, M Medium, U Ultra Deep			
VISCOSITY@77°F/25°C (ASTM D 562): 90–100 KU			
MAXIMUM VOC CONTENT 50 g/L (as supplied)		MAXIMUM RAVOC (Reactivity-Adjusted VOC) 20 g/L	
SOLIDS BY VOLUME (ASTM D 2697) 35.0% ± 2%		SOLIDS BY WEIGHT 46.0% ± 2%	
WEIGHT PER GALLON (ASTM D 1475): 10.16 lbs.			
COMPOSITION BY WEIGHT			
Pigment–21.4%		Vehicle–78.6%	
*Prime pigments16.2		Acrylic resins22.5	
Reinforcing pigments5.2		Water & additives56.1	
<i>*Prime pigments include titanium dioxide (TiO₂), plus all other pigments directly adding to the hiding power of this paint.</i>			
RECOMMENDED FILM THICKNESS PER COAT			
Wet: 4.3 mils		Dry: 1.5 mils	
PRACTICAL COVERAGE PER COAT AT RECOMMENDED DRY FILM THICKNESS Approximately 325–375 sq. ft. per gallon, depending on surface conditions and application techniques.			
THINNING RECOMMENDATION: This coating is intended to be applied without thinning or diluting under normal environmental and application conditions. If necessary to maintain good workability, add up to 1/4 pint (4 fl. oz.) of clean water per gallon of coating.			
AVERAGE DRY TIME@77°F/25°C (ASTM D 1640)			
To touch: 1–2 hours		Recoat: 4–6 hours	
Dry times and recoat times are temperature, humidity and film thickness dependent.			
APPLICATION EQUIPMENT: Brush, roller, airless spray			
PACKAGING: One-gallon, five-gallon containers			
STORAGE: Store in a dry area. Protect from freezing. Protect from temperatures above 110°F for extended periods of time. Extreme temperatures may cause paint to become unusable. <i>See Paint Storage Best Practices</i> Technical Bulletin at dunnedwards.com for more information.			
CLEANUP: Warm, soapy water			
DISPOSAL: For information on local options to dispose of unwanted leftover paint, call Dunn-Edwards Customer Service at 1-888-DEPAINT or visit www.dunnedwards.com . Do not mix with other products.			
CONFORMS TO: ARB 2007 SCM & CAL Green 2013; MPI Approved Product #11			
SAFETY DATA SHEET: Available at www.dunnedwards.com			
SURFACE PREPARATION: All surfaces must be cured, clean, dry, and free from dirt, dust, rust, stains, grease, oil, mildew, wax, efflorescence, bond-breakers, and other contaminants. Remove all loose, peeling, or chalky paint by sanding, scraping, or other appropriate methods. Repair all cracks, holes, and other surface imperfections with a suitable patching material. Repaired surfaces should then be sanded smooth and dusted clean. Glossy surfaces should be dulled to provide a roughened surface for good adhesion.			

SPECIAL INSTRUCTIONS

- **CAUTION:** Scraping or sanding surfaces of older buildings (especially pre-1978) may release dust containing lead or asbestos. EXPOSURE TO LEAD OR ASBESTOS CAN BE VERY HAZARDOUS TO YOUR HEALTH. Always wear appropriate personal protective equipment during surface preparation, and finish cleanup of any residues by water-washing all surfaces. For more information, see Dunn-Edwards brochure on “Surface Preparation Safety” or call EPA’s National Lead Information Hotline at 1-800-424-LEAD, or log onto www.epa.gov/lead/or/asbestos, or contact your state or local Health Department.
- This product can neither cause nor prevent or cure the growth of mold, mildew, or other forms of fungus. Excessive moisture and inadequate ventilation are the main conditions that promote their growth. Correct any such conditions before painting.
- If efflorescence exists, remove all noticeable deposits and prime the entire surface with **SUPER-LOC® Premium (SLPR00)**, **EFF-STOP® Premium (ESPR00)** or **EFF-STOP® Select (ESSL00)**.
- Certain woods, such as redwood, cedar, and spruce, contain water-soluble extracts (tannins) that may discolor lighter colors. In these situations, it is recommended to prime the wood with **EZ-PRIME® Premium (EZPR00)** before applying **ACRI-HUES® Semi-Gloss (ACHS50)**.
- For best results, use airless spray application.
- When the air temperature is at 35°F, substrates may be colder; prior to painting, check to be sure the air, surface, and material temperature are above 35°F and at least 5°F above the dew point. Avoid using if rain or snow is expected within 2-3 hours, as in colder temperatures, it may require longer time before the paint film cures enough not to be affected by rain or snow. Do not apply at air or surface temperatures below 35°F or when air or surface temperatures may drop below 35°F within 48 hours.
- Standard latex primers cannot be used below 50°F. See the specific primer product information sheet for that product’s application conditions.

PRIMERS

MASONRY

Plaster:	}	EFF-STOP® Premium (ESPR00), EFF-STOP® Select (ESSL00) or FLEX-PRIME® Select (FPFL00)
Tilt-up concrete:		
Poured-in-place:		
Brick:		
Concrete block:		Smooth BLOCFIL Premium (SBPR00), Smooth BLOCFIL Select (SBSL00) or FLEX-PRIME® Select (FPFL00)

WOOD

Trim, sash, fascia:	}	EZ-PRIME® Premium (EZPR00)
T1-11 siding:		
Rough-sawn:		Self-priming (see SPECIAL INSTRUCTIONS)

SYNTHETIC WOOD

Masonite:	}	ULTRA-GRIP® Premium (UGPR00) or ULTRA-GRIP® Select (UGSL00)
Hardboard:		
MDO siding:		

METAL

Ferrous:	BLOC-RUST® Premium (BRPR00) or ULTRASHIELD® Galvanized Metal Primer (ULGM00)
Non-ferrous:	ULTRASHIELD® Galvanized Metal Primer (ULGM00) or ULTRA-GRIP® Premium (UGPR00) or ULTRA-GRIP® Select (UGSL00)