



THE #1 CHOICE OF
PAINTING PROFESSIONALS®

AQUAFALL®

Latex Dry Fall Flat AQUA10-1



DESCRIPTION: AQUAFALL® Flat is a premium fast drying, non-bridging waterborne dry fall (dry fog) flat coating designed for interior ceilings, acoustic tiles and overhead surfaces. AQUAFALL Flat is ideal for commercial warehouses, factories, retail outlets, hangars, parking structures, and other facilities where overspray cannot be tolerated. AQUAFALL Flat exhibits very good adhesion to galvanized heating ducts, foil-wrapped ducts, steel girders, masonry, and wood. AQUAFALL Flat has a dry fall distance of approximately ten feet under normal conditions.

PRODUCT INFORMATION

SOLVENT TYPE: Waterborne **RESIN TYPE:** Acrylic copolymer

FINISH (ASTM D 523): Flat: <2.5% on a 60° meter; <2.5% on an 85° meter

COLORS: White and Black. Other colors can be special ordered or store mixed.

TINT BASES: Tintable White (WH), U Ultra Deep

VISCOSITY@77°F/25°C (ASTM D 562): 80–90 KU

MAXIMUM VOC CONTENT 35 g/L (as supplied)	MAXIMUM RAVOC (Reactivity-Adjusted VOC) 10 g/L
--	--

SOLIDS BY VOLUME (ASTM D 2697) 43.2% ± 2%	SOLIDS BY WEIGHT 62.5% ± 2%
---	---------------------------------------

WEIGHT PER GALLON (ASTM D 1475): 12.78 lbs.

COMPOSITION BY WEIGHT

Pigment–53.3%	Vehicle–46.7%
*Prime pigments5.5	Vinyl acrylic resins8.0
Reinforcing pigments47.8	Water & additives38.7

**Prime pigments include titanium dioxide (TiO₂), plus all other pigments directly adding to the hiding power of this paint.*

RECOMMENDED FILM THICKNESS PER COAT

Wet: 3.5 mils Dry: 1.5 mils

PRACTICAL COVERAGE PER COAT AT RECOMMENDED DRY FILM THICKNESS
Approximately 400–450 sq. ft. per gallon, depending on surface conditions and application techniques.

THINNING RECOMMENDATION: This coating is intended to be applied without thinning or diluting under normal environmental and application conditions. If necessary to maintain good workability, add up to 1/4 pint (4 fl. oz.) of clean water per gallon of coating.

AVERAGE DRY TIME@77°F/25°C (ASTM D 1640)

To touch: 15-45 minutes Recoat: 2 hours
Dry times and recoat times are temperature, humidity and film thickness dependent.

APPLICATION EQUIPMENT: Airless spray

PACKAGING: Five-gallon containers

STORAGE: Store in a dry area. Protect from freezing. Protect from temperatures above 110°F for extended periods of time. Extreme temperatures may cause paint to become unusable. See *Paint Storage Best Practices* Technical Bulletin at dunnedwards.com for more information.

CLEANUP: Warm, soapy water

DISPOSAL: For information on local options to dispose of unwanted leftover paint, call Dunn-Edwards Customer Service at 1-888-DEPAINT or visit www.dunnedwards.com. **Do not mix with other products.**

CONFORMS TO: ARB 2007 SCM & CALGreen 2013; LEED 2009 IEQ Credit 4.2; LEED v4 EQ Credit 2

SAFETY DATA SHEET: Available at www.dunnedwards.com

SURFACE PREPARATION: All surfaces must be cured, clean, dry, and free from dirt, dust, rust, stains, grease, oil, mildew, wax, efflorescence, bond-breakers, and other contaminants. Remove all loose, peeling, or chalky paint by sanding, scraping, or other appropriate methods. Repair all cracks, holes, and other surface imperfections with a suitable patching material. Repaired surfaces should then be sanded smooth and dusted clean. Glossy surfaces should be dulled to provide a roughened surface for good adhesion.

SPECIAL INSTRUCTIONS

- CAUTION: Scraping or sanding surfaces of older buildings (especially pre-1978) may release dust containing lead or asbestos. EXPOSURE TO LEAD OR ASBESTOS CAN BE VERY HAZARDOUS TO YOUR HEALTH. Always wear appropriate personal protective equipment during surface preparation, and finish cleanup of any residues by water-washing all surfaces. For more information, see Dunn-Edwards brochure on "Surface Preparation Safety" or call EPA's National Lead Information Hotline at 1-800-424-LEAD, or log onto www.epa.gov/lead or/asbestos, or contact your state or local Health Department.
- This product can neither cause nor prevent or cure the growth of mold, mildew, or other forms of fungus. Excessive moisture and inadequate ventilation are the main conditions that promote their growth. Correct any such conditions before painting.
- Surface must be dry and at least 5° above the dew point.
- Do not apply when the air or surface temperature is below 50°F.

LIMITATIONS

- Not for exterior exposure
- Not for high abuse surfaces
- Not for high corrosion areas
- Not for areas with high humidity