



THE #1 CHOICE OF
PAINTING PROFESSIONALS®

SUPER U-365®

Interior Fire Retardant Alkyd Enamel Undercoater E 22-1A



DESCRIPTION: SUPER U-365® is a premium fire retardant alkyd undercoater designed to provide excellent sealing, adhesion, and enamel holdout. SUPER U-365 is recommended as a primer on new drywall, wood, and synthetic wood, and as an intermediate coat on previously sealed surfaces, in interior areas where fire safety is a concern. SUPER U-365 sands very easily and provides excellent hide. Within California, available only in quarts. **RECOMMENDED FOR PROFESSIONAL USE ONLY.**

PRODUCT INFORMATION

SOLVENT TYPE: Paint thinner | **RESIN TYPE:** Alkyd

FINISH (ASTM D 523): 0.0–10% on a 60° meter

COLORS: White. SUPER U-365® may be tinted with up to 2 fl. oz. of Dunn-Edwards ZTC Zero VOC colorant per gallon.

VISCOSITY@77°F/25°C (ASTM D 562): 95–100 KU

MAXIMUM VOC CONTENT 350 g/L (as supplied) | **MAXIMUM RAVOC** (Reactivity-Adjusted VOC) 125 g/L

SOLIDS BY VOLUME (ASTM D 2697) 55.1% ± 2% | **SOLIDS BY WEIGHT** 76.0% ± 2%

WEIGHT PER GALLON (ASTM D 1475): 12.23 lbs.

COMPOSITION BY WEIGHT

Pigment—57.3%		Vehicle—42.7%	
*Prime pigments	15.7	Alkyd resins	17.8
Fire retardant pigment	4.0	Thinner & additives	24.9
Reinforcing pigments	37.6		

*Prime pigments include titanium dioxide (TiO₂), plus all other pigments directly adding to the hiding power of this paint.

RECOMMENDED FILM THICKNESS PER COAT

Wet: 3.6 mils | Dry: 2.0 mils

PRACTICAL COVERAGE PER COAT AT RECOMMENDED DRY FILM THICKNESS

Approximately 375–425 sq. ft. per gallon, depending on surface conditions and application techniques.

THINNING RECOMMENDATION: This coating is intended to be applied without thinning or diluting under normal environmental and application conditions.

AVERAGE DRY TIME@77°F/25°C (ASTM D 1640)

To touch: 2–4 hours | Recoat: 24 hours
Dry times and recoat times are temperature, humidity and film thickness dependent.

APPLICATION EQUIPMENT: Brush, roller, airless spray

PACKAGING: Quart, one-gallon, five-gallon containers

STORAGE: Store in a dry area. Protect from freezing. Protect from temperatures above 110°F for extended periods of time. Extreme temperatures may cause paint to become unusable. See *Paint Storage Best Practices* Technical Bulletin at dunnedwards.com for more information.

CLEANUP: Paint thinner where allowed. Otherwise, use acetone.

DISPOSAL: For information on local options to dispose of unwanted leftover paint, call Dunn-Edwards Customer Service at 1-888-DEPAINT or visit www.dunnedwards.com. **Do not mix with other products.**

CONFORMS TO: FDA Guidelines for Resinous & Polymeric Coatings

SAFETY DATA SHEET: Available at www.dunnedwards.com

SURFACE PREPARATION: All surfaces must be cured, clean, dry, and free from dirt, dust, rust, stains, grease, oil, mildew, wax, efflorescence, bond-breakers, and other contaminants. Remove all loose, peeling, or chalky paint by sanding, scraping, or other appropriate methods. Repair all cracks, holes, and other surface imperfections with a suitable patching material. Repaired surfaces should then be sanded smooth and dusted clean. Glossy surfaces should be dulled to provide a roughened surface for good adhesion.

This Fire Retardant Coating has been fire-tested in accordance with ASTM Designation E 84-04 and rated as NFPA Class A, UBC Class I, with a flame spread index of 25 and smoke developed value of 10. Test report available upon request.

IMPORTANT: Fire Retardant Coatings do not make combustible materials fireproof. The purpose of a Fire Retardant is to delay ignition and flame spread, providing valuable time for fire response or escape.

SPECIAL INSTRUCTIONS

- **CAUTION:** Scraping or sanding surfaces of older buildings (especially pre-1978) may release dust containing lead or asbestos. EXPOSURE TO LEAD OR ASBESTOS CAN BE VERY HAZARDOUS TO YOUR HEALTH. Always wear appropriate personal protective equipment during surface preparation, and finish cleanup of any residues by water-washing all surfaces. For more information, see Dunn-Edwards brochure on “Surface Preparation Safety” or call EPA’s National Lead Information Hotline at 1-800-424-LEAD, or log onto www.epa.gov/lead or/asbestos, or contact your state or local Health Department.
- This product can neither cause nor prevent or cure the growth of mold, mildew, or other forms of fungus. Excessive moisture and inadequate ventilation are the main conditions that promote their growth. Correct any such conditions before painting.
- SUPER U-365® is intended for use in conjunction with ARISTOGLO® Interior Fire Retardant Alkyd Semi-Gloss Enamel (74A).
- Do not apply when the air or surface temperature is below 50°F.

CALIFORNIA PROPOSITION 65 NOTICE:

⚠ WARNING: This product can expose you to ethylbenzene, which is known to the State of California to cause cancer. For more information go to www.P65Warnings.ca.gov.

USE AS A PRIMER FOR

DRYWALL

Textured: }
 Untextured: } **SUPER U-365® (E 22-1A)**
 Skim-coated: }

WOOD

Trim, doors: **SUPER U-365® (E 22-1A)**

SYNTHETIC WOOD

Masonite: }
 Hardboard: } **SUPER U-365® (E 22-1A)**