



THE #1 CHOICE OF
PAINTING PROFESSIONALS®

EZ-PRIME® Premium

Exterior Wood Primer EZPR00



≤ 50 g/L VOC*

DESCRIPTION: EZ-PRIME® Premium is an exterior acrylic primer that provides excellent enamel holdout and tannin stain resistance on woods such as redwood and cedar, which are subject to stain bleeding. EZ-PRIME Premium is also recommended on exterior plywood and T1-11 siding.

PRODUCT INFORMATION

SOLVENT TYPE: Waterborne		RESIN TYPE: Acrylic	
FINISH (ASTM D 523): 7–17% on a 60° meter			
COLORS: White. EZ-PRIME Premium may be tinted with up to 2 fl. oz. of Dunn-Edwards ZTC Zero VOC colorant per gallon.			
VISCOSITY@77°F/25°C (ASTM D 562): 87–97 KU			
MAXIMUM VOC CONTENT 50 g/L (as supplied)		MAXIMUM RAVOC (Reactivity-Adjusted VOC) 20 g/L	
SOLIDS BY VOLUME (ASTM D 2697) 41.0% ± 2%		SOLIDS BY WEIGHT 54.0% ± 2%	
WEIGHT PER GALLON (ASTM D 1475): 10.50 lbs.			
COMPOSITION BY WEIGHT			
Pigment–27.1%		Vehicle–72.9%	
*Prime pigments 14.4		Acrylic resins 23.7	
Reinforcing pigments 12.7		Water & additives 49.2	
<i>*Prime pigments include titanium dioxide (TiO₂), plus all other pigments directly adding to the hiding power of this paint.</i>			
RECOMMENDED FILM THICKNESS PER COAT			
Wet: 4.9 mils		Dry: 2.0 mils	
PRACTICAL COVERAGE PER COAT AT RECOMMENDED DRY FILM THICKNESS Approximately 275–325 sq. ft. per gallon, depending on surface conditions and application techniques.			
THINNING RECOMMENDATION: This coating is intended to be applied without thinning or diluting under normal environmental and application conditions. If necessary to maintain good workability, add up to 1/4 pint (4 fl. oz.) of clean water per gallon of coating.			
AVERAGE DRY TIME@77°F/25°C (ASTM D 1640) To touch: 30–60 minutes Recoat: 2–4 hours (see Special Instructions) Dry times and recoat times are temperature, humidity and film thickness dependent.			
APPLICATION EQUIPMENT: Brush, roller, airless spray			
PACKAGING: Quart, one-gallon, five-gallon containers			
STORAGE: Store in a dry area. Protect from freezing. Protect from temperatures above 110°F for extended periods of time. Extreme temperatures may cause paint to become unusable. See Paint Storage Best Practices Technical Bulletin at dunnedwards.com for more information.			
CLEANUP: Warm, soapy water			
DISPOSAL: For information on local options to dispose of unwanted leftover paint, call Dunn-Edwards Customer Service at 1-888-DEPAINT or visit www.dunnedwards.com . Do not mix with other products.			
CONFORMS TO: ARB 2007 SCM & CALGreen 2016; MPI Approved Product #6; CRGI Green Wise Certified			
SAFETY DATA SHEET: Available at www.dunnedwards.com			
SURFACE PREPARATION: All surfaces must be cured, clean, dry, and free from dirt, dust, rust, stains, grease, oil, mildew, wax, efflorescence, bond-breakers, and other contaminants. Remove all loose, peeling, or chalky paint by sanding, scraping, or other appropriate methods. Repair all cracks, holes, and other surface imperfections with a suitable patching material. Repaired surfaces should then be sanded smooth and dusted clean. Glossy surfaces should be dulled to provide a roughened surface for good adhesion.			

SPECIAL INSTRUCTIONS

- CAUTION!** Scraping or sanding surfaces of older buildings (especially pre-1978) may release dust containing lead or asbestos. EXPOSURE TO LEAD OR ASBESTOS CAN BE VERY HAZARDOUS TO YOUR HEALTH. Wear a NIOSH-approved N95 particulate filter mask to avoid breathing dust. Use a HEPA vacuum for cleanup, and finish by water-washing all surfaces. For more information, see Dunn-Edwards brochure on "Surface Preparation Safety" or call U.S. EPA's lead hotline at 1-800-424-LEAD, or visit www.epa.gov/lead or / asbestos, or contact your state or local Health Agency.
- This product can neither cause nor prevent or cure the growth of mold, mildew, or other forms of fungus. Excessive moisture and inadequate ventilation are the main conditions that promote their growth. Correct any such conditions before painting.
- Exterior wood may be allowed to contain no more than 15% moisture. Painting over wood with excessively high moisture content can result in loss of adhesion, blistering, peeling, cracking, and discoloration.
- Apply two coats of EZ-PRIME® Premium on redwood and cedar in order to stop tannin bleeding. Allow first coat to dry for 24 hours before applying the second coat.
- Do not apply when the air or surface temperature is below 50°F.

USE AS A PRIMER FOR

WOOD

Trim, sash, fascia: }
Rough-sawn: } **EZ-PRIME® Premium (EZPR00)**
T1-11 siding: }
Plywood: }

SYNTHETIC WOOD

Masonite: }
Hardboard: } **EZ-PRIME® Premium (EZPR00)**
MDO siding: }

**This product has been tested and certified by Coatings Research Group Inc., an international paint industry-organized ISO-accredited testing laboratory, to meet performance and environmental standards as shown on www.greenwisepaint.com. Dunn-Edwards is a member of CRGI.*

HEALTH & SAFETY: CAUTIONS! INHALATION OF SPRAY MIST OR SANDING DUST MAY BE HARMFUL. Use only with adequate ventilation. Avoid breathing vapors, spray mist and sanding dust. Wear NIOSH-approved N95 particulate filter mask when spraying or sanding. Avoid contact with skin and eyes. Do not ingest. Close container after each use. **FIRST AID:** If swallowed, immediately give 1 or 2 glasses of water to drink – for emergency information, call 1-800-222-1222. If having difficulty breathing, move to fresh air. For eye contact, immediately flush with water for 15 minutes. For skin contact, wash thoroughly with soap and water.

• KEEP OUT OF REACH OF CHILDREN •

Ingredient (CAS #): Water (7732-18-5); Copolymer Resin (Proprietary); Titanium Dioxide (13463-67-7); Nepheline Syenite (37244-96-5); Talc, Non-Asbestos (14807-96-6).

⚠ WARNING: Cancer and Reproductive Harm – www.P65Warnings.ca.gov