



THE #1 CHOICE OF
PAINTING PROFESSIONALS.®

SUPER-LOC® Premium

Interior/Exterior Masonry/Bonding Primer

SLPR00-2-WH



DESCRIPTION: SUPER-LOC® Premium is an ultra premium, high performance, ultra-low VOC, low odor, interior and exterior masonry/bonding primer. It provides excellent adhesion to difficult-to-paint surfaces: tile, porcelain, ferrous metal (interior only), non-ferrous metal (aluminum, brass, copper), most plastics, Formica, fiberglass, glass, aged alkyds, hardboard, wallboard, cabinets, chalky surfaces (mild to moderate), PVC piping, fiber cement. SUPER-LOC Premium also provides excellent adhesion and outstanding resistance to alkali and efflorescence on properly cured masonry: tilt-up concrete, poured-in-place concrete, rough stucco, smoothed-troweled stucco.

PRODUCT INFORMATION

| | | | |
|--|--|--|--|
| SOLVENT TYPE: Waterborne | | RESIN TYPE: Urethane Modified Acrylic | |
| FINISH (ASTM D 523): 18–28% on a 60° meter | | | |
| COLORS: White. SUPER-LOC Premium may be tinted with up to 2 fl. oz. of Dunn-Edwards ZTC Zero VOC colorant per gallon. | | | |
| VISCOSITY@77°F/25°C (ASTM D 562): 85–95 KU | | | |
| MAXIMUM VOC CONTENT 50 g/L (as supplied) | MAXIMUM RAVOC (Reactivity-Adjusted VOC) 25 g/L | | |
| SOLIDS BY VOLUME (ASTM D 2697) 33.6% ± 2% | SOLIDS BY WEIGHT 43.8% ± 2% | | |
| WEIGHT PER GALLON (ASTM D 1475): 9.81 lbs. | | | |

| | |
|---|-----------------------------|
| COMPOSITION BY WEIGHT | |
| Pigment—17.6% | Vehicle—82.4% |
| *Prime pigments10.5 | Acrylic resins23.1 |
| Reinforcing pigments7.1 | Water & additives59.3 |
| <i>*Prime pigments include titanium dioxide (TiO₂), plus all other pigments directly adding to the hiding power of this paint.</i> | |

| | |
|--|---------------|
| RECOMMENDED FILM THICKNESS PER COAT | |
| Wet: 5.9 mils | Dry: 2.0 mils |

PRACTICAL COVERAGE PER COAT AT RECOMMENDED DRY FILM THICKNESS
Approximately 200–275 sq. ft. per gallon, depending on surface conditions and application techniques.

THINNING RECOMMENDATION: This coating is intended to be applied without thinning or diluting under normal environmental and application conditions. If necessary to maintain good workability, add up to 1/4 pint (4 fl. oz.) of clean water per gallon of coating.

| | |
|--|-------------------|
| AVERAGE DRY TIME@77°F/25°C (ASTM D 1640) | |
| To touch: 30–60 minutes | Recoat: 2–4 hours |
| Dry times and recoat times are temperature, humidity and film thickness dependent. | |

APPLICATION EQUIPMENT: Brush, roller, airless spray

PACKAGING: One-gallon, five-gallon containers

STORAGE: Store in a dry area. Protect from freezing. Protect from temperatures above 110°F for extended periods of time. Extreme temperatures may cause paint to become unusable. See *Paint Storage Best Practices* Technical Bulletin at dunnedwards.com for more information.

CLEANUP: Warm, soapy water

DISPOSAL: For information on local options to dispose of unwanted leftover paint, call Dunn-Edwards Customer Service at 1-888-DEPAINT or visit www.dunnedwards.com. **Do not mix with other products.**

CONFORMS TO: ARB 2007 SCM & CALGreen 2016; LEED 2009 IEQ Credit 4.2; FDA Guidelines for Resinous & Polymeric Coatings

SAFETY DATA SHEET: Available at www.dunnedwards.com

SURFACE PREPARATION: All surfaces must be cured, clean, dry, and free from dirt, dust, rust, stains, grease, oil, mildew, wax, efflorescence, bond-breakers, and other contaminants. Remove all loose, peeling, or chalky paint by sanding, scraping, or other appropriate methods. Repair all cracks, holes, and other surface imperfections with a suitable patching material. Repaired surfaces should then be sanded smooth and dusted clean. Glossy surfaces should be dulled to provide a roughened surface for good adhesion.

SPECIAL INSTRUCTIONS

- **CAUTION:** Scraping or sanding surfaces of older buildings (especially pre-1978) may release dust containing lead or asbestos. EXPOSURE TO LEAD OR ASBESTOS CAN BE VERY HAZARDOUS TO YOUR HEALTH. Always wear appropriate personal protective equipment during surface preparation, and finish cleanup of any residues by water-washing all surfaces. For more information, see Dunn-Edwards brochure on “Surface Preparation Safety” or call EPA’s National Lead Information Hotline at 1-800-424-LEAD, or visit www.epa.gov/lead or /asbestos, or contact your state or local Health Department.
- This product can neither cause nor prevent or cure the growth of mold, mildew, or other forms of fungus. Excessive moisture and inadequate ventilation are the main conditions that promote their growth. Correct any such conditions before painting.
- Due to the various types of surfaces, always test a few different areas for adhesion.
- For exterior ferrous metal, use **BLOC-RUST Premium (BRPR00)**.
- Do not apply when the air or surface temperature is below 50°F.

USE AS A PRIMER FOR

MASONRY: SUPER-LOC® Premium can be applied on surfaces with a pH of up to 13.

| | |
|-------------------|--------------------------------------|
| Plaster: | } SUPER-LOC® Premium (SLPR00) |
| Brick: | |
| Stucco (new): | |
| Stucco (repaint): | |
| Tilt-up concrete: | |
| Poured-in-place: | |
| Smooth trowel: | |

METAL:

| | |
|-------------------|--|
| Ferrous: | BLOC-RUST® Premium (BRPR00) or ENDURAPRIME® Metal Primer (ENPR00) |
| Non-ferrous: | ULTRASHIELD® Galvanized Metal Primer (ULGM00) or BLOC-RUST® Premium (BRPR00) |
| Galvanized steel: | ULTRASHIELD® Galvanized Metal Primer (ULGM00) or *ULTRA-GRIP® Premium (UGPR00) |

**for incidental use on galvanized*

OTHER SURFACES

| | |
|-------------------------------------|--------------------------------------|
| Tile: | } SUPER-LOC® Premium (SLPR00) |
| Porcelain: | |
| Most plastics: | |
| Formica | |
| Fiberglass: | |
| Glass: | |
| Aged alkyds: | |
| Hardboard: | |
| Wallboard: | |
| Cabinets: | |
| Chalky surfaces (mild to moderate): | |
| PVC piping: | |
| Fiber cement: | |