



THE #1 CHOICE OF
PAINTING PROFESSIONALS®

VINYLASTIC® Select

Interior
Wall Sealer

VNSL00-1



DESCRIPTION: VINYLASTIC® Select is a Zero VOC, low odor water-based sealer that has excellent sealing qualities on new drywall. It is easy to apply and dries fast for same day finishing.

PRODUCT INFORMATION

SOLVENT TYPE: Waterborne | **RESIN TYPE:** Acrylic copolymer

FINISH (ASTM D 523): 6–10% on a 60° meter

COLORS: White. VINYLASTIC Select may be tinted with up to 2 fl. oz. of Dunn-Edwards ZTC Zero VOC colorant per gallon.

VISCOSITY@77°F/25°C (ASTM D 562): 81–91 KU

MAXIMUM VOC CONTENT | **MAXIMUM RAVOC** (Reactivity-Adjusted VOC)
4 g/L (by ASTM Test Method D 6886) | 4 g/L

NOTE: “Zero VOC” means “No organic solvents added.” (Trace amounts of VOC may be present as residual components of other ingredients. Dunn-Edwards uses Zero VOC colorants; other additives may increase VOC emissions.)

SOLIDS BY VOLUME (ASTM D 2697) | **SOLIDS BY WEIGHT**
30.5% ± 2% | 41.3% ± 2%

WEIGHT PER GALLON (ASTM D 1475): 10.40 lbs.

COMPOSITION BY WEIGHT

Pigment–23.5%		Vehicle–76.5%	
*Prime pigments	11.6	Vinyl acrylic resins	15.9
Reinforcing pigments	11.9	Water & additives	60.6
*Prime pigments include titanium dioxide (TiO ₂), plus all other pigments directly adding to the hiding power of this paint.			

RECOMMENDED FILM THICKNESS PER COAT

Wet: 6.5 mils | Dry: 2.0 mils

PRACTICAL COVERAGE PER COAT AT RECOMMENDED DRY FILM THICKNESS
Approximately 175–225 sq. ft. per gallon, depending on surface conditions and application techniques.

THINNING RECOMMENDATION

Brush application: Do not thin
Roller application: Up to 1/2 pint of water per gallon
Spray application: Up to 1 pint of water per gallon

AVERAGE DRY TIME@77°F/25°C

To touch: 30–60 minutes | Recoat: 2–4 hours
Dry times and recoat times are temperature, humidity and film thickness dependent.

APPLICATION EQUIPMENT: Brush, roller, airless spray

PACKAGING: Five-gallon containers

STORAGE: Store in a dry area. Protect from freezing. Protect from temperatures above 110°F for extended periods of time. Extreme temperatures may cause paint to become unusable. See **Paint Storage Best Practices** Technical Bulletin at dunnedwards.com for more information.

CLEANUP: Warm, soapy water

DISPOSAL: For information on local options to dispose of unwanted leftover paint, call Dunn-Edwards Customer Service at 1-888-DEPAINT or visit www.dunnedwards.com. **Do not mix with other products.**

CONFORMS TO: ARB 2007 SCM & CALGreen 2013; CHPS Section 01350; LEED 2009 IEQ Credit 4.2; LEED v4 EQ Credit 2; MPI Approved Product #50; CRGI Green Wise Certified Gold

SAFETY DATA SHEET: Available at www.dunnedwards.com

SURFACE PREPARATION: All surfaces must be cured, clean, dry, and free from dirt, dust, rust, stains, grease, oil, mildew, wax, efflorescence, bond-breakers, and other contaminants. Remove all loose, peeling, or chalky paint by sanding, scraping, or other appropriate methods. Repair all cracks, holes, and other surface imperfections with a suitable patching material. Repaired surfaces should then be sanded smooth and dusted clean. Glossy surfaces should be dulled to provide a roughened surface for good adhesion.

SPECIAL INSTRUCTIONS

- CAUTION: Scraping or sanding surfaces of older buildings (especially pre-1978) may release dust containing lead or asbestos. EXPOSURE TO LEAD OR ASBESTOS CAN BE VERY HAZARDOUS TO YOUR HEALTH. Always wear appropriate personal protective equipment during surface preparation, and finish cleanup of any residues by water-washing all surfaces. For more information, see Dunn-Edwards brochure on “Surface Preparation Safety” or call EPA’s National Lead Information Hotline at 1-800-424-LEAD, or visit www.epa.gov/lead or /asbestos, or contact your state or local Health Department.
- This product can neither cause nor prevent or cure the growth of mold, mildew, or other forms of fungus. Excessive moisture and inadequate ventilation are the main conditions that promote their growth. Correct any such conditions before painting.
- New, untextured drywall is frequently covered with powdery and unstable joint compound. When this condition exists, using waterborne sealers, such as VINYLASTIC® Select, can result in adhesion problems. After removing excess dust, it is recommended VINYLASTIC® Select be applied to a small test area to verify proper adhesion.
- Not recommended for sealing beneath vinyl wallcovering.
- Allow all skim coats to cure for 3 days before sealing.
- Check newly applied plaster for alkalinity with phenolphthalein. The surface color will change to purple when excess alkali is present. Remove alkali by washing the plaster with phosphoric acid solution diluted with water. Rinse plaster with clean water to remove all traces of the acid solution, then retest before proceeding.
- For sealing pigment-rich skim coats, such as “Prep Coat” and “First Coat,” use Spartawall® (SWLL10).
- Do not apply when the air or surface temperature is below 50°F.

USE AS A SEALER FOR

DRYWALL

Textured: VINYLASTIC® Select (VNSL00)
 Untextured: VINYLASTIC® Select (VNSL00) (see *Special Instructions*)
 Skim-coated: VINYLASTIC® Select (VNSL00) or SPARTAWALL® Flat (SWLL10) (see *Special Instructions*)