



THE #1 CHOICE OF
PAINTING PROFESSIONALS®

ENDURASEAL®

100% Acrylic
Masonry Sealer
W 360V



DESCRIPTION: ENDURASEAL® is a premium acrylic semi-transparent sealer designed for use on smooth troweled plaster, stucco, and concrete. ENDURASEAL provides excellent adhesion and is a recommended sealer for **Endurawall (W 370)** and **Enduralastic – Elastomeric Coating lines**. ENDURASEAL dries to a milky-clear finish (See Special Instructions).

PRODUCT INFORMATION

SOLVENT TYPE: Waterborne **RESIN TYPE:** 100% acrylic

FINISH (ASTM D 523): Flat

COLORS: Slightly opaque, milky when dry.

VISCOSITY@77°F/25°C (Zahn Cup #2): 12–18 sec.

MAXIMUM VOC CONTENT 50 g/L (as supplied)	MAXIMUM RAVOC (Reactivity-Adjusted VOC) 15 g/L
--	--

SOLIDS BY VOLUME (ASTM D 2697) 19.6% ± 2%	SOLIDS BY WEIGHT 17.9% ± 2%
---	---------------------------------------

WEIGHT PER GALLON (ASTM D 1475): 8.45 lbs.

COMPOSITION BY WEIGHT

Pigment–3.7% *Prime pigments3.7	Vehicle–96.3% Acrylic resins13.4 Thinner & additives82.9
---	---

*Prime pigments include titanium dioxide (TiO₂), plus all other pigments directly adding to the hiding power of this paint.

RECOMMENDED FILM THICKNESS PER COAT

Wet: 8.8 mils Dry: 1.5 mils

PRACTICAL COVERAGE PER COAT AT RECOMMENDED DRY FILM THICKNESS

Approximately 100–150 sq. ft. per gallon, depending on surface conditions and application techniques.

THINNING RECOMMENDATION: This coating is intended to be applied without thinning or diluting under normal environmental and application conditions. If necessary to maintain good workability, add up to 1/4 pint (4 fl. oz.) of clean water per gallon of coating.

AVERAGE DRY TIME@77°F/25°C (ASTM D 1640)

To touch: 30–60 minutes Recoat: 2–4 hours

APPLICATION EQUIPMENT: Brush, roller, airless spray

PACKAGING: Five-gallon containers

STORAGE: Store in a dry area. Protect from freezing. Extreme temperatures may cause paint to become unusable. For example: freezing and thawing may cause paint to gel, and high heat may cause solid skin to form.

CLEANUP: Warm, soapy water

DISPOSAL: For information on local options to dispose of unwanted leftover paint, call Dunn-Edwards Customer Service at 1-888-DEPAINT or visit www.dunnedwards.com. **Do not mix with other products.**

SAFETY DATA SHEET: Available at www.dunnedwards.com

SURFACE PREPARATION: All surfaces must be cured, clean, dry, and free from dirt, dust, rust, stains, grease, oil, mildew, wax, efflorescence, bond-breakers, and other contaminants. Remove all loose, peeling, or chalky paint by sanding, scraping, or other appropriate methods. Repair all cracks, holes, and other surface imperfections with a suitable patching material. Repaired surfaces should then be sanded smooth and dusted clean. Glossy surfaces should be dulled to provide a roughened surface for good adhesion.

SPECIAL INSTRUCTIONS

- CAUTION: Scraping or sanding surfaces of older buildings (especially pre-1978) may release dust containing lead or asbestos. EXPOSURE TO LEAD OR ASBESTOS CAN BE VERY HAZARDOUS TO YOUR HEALTH. Always wear appropriate personal protective equipment during surface preparation, and finish cleanup of any residues by water-washing all surfaces. For more information, see Dunn-Edwards brochure on “Surface Preparation Safety” or call EPA’s National Lead Information Hotline at 1-800-424-LEAD, or log onto www.epa.gov/lead or/asbestos, or contact your state or local Health Department.
- This product can neither cause nor prevent or cure the growth of mold, mildew, or other forms of fungus. Excessive moisture and inadequate ventilation are the main conditions that promote their growth. Correct any such conditions before painting.
- Stucco and smooth troweled plaster should cure at least 3 days before applying ENDURASEAL.
- Tilt-up concrete should cure at least 7 days before application.
- ENDURASEAL is not designed to achieve hide and should not be applied heavily enough to achieve hide. The milky-clear finish indicates to the operator the areas that have been sealed.
- Do not apply when the air or surface temperature is below 50°F.

USE AS A SEALER FOR

MASONRY

Stucco (new):	}	SUPER-LOC® Premium (SLPR00) or Enduraseal® (W 360V)
Stucco (repaint):		
Tilt-up concrete:		
Poured-in-place:		
Brick:		
Smooth trowel:	}	Smooth BLOCFIL Premium (SBPR00)
Concrete block:		